

## TEST REPORT

APPLICANT : QINGDAO TAEHOON STEEL PIPE INC.

REPORT NO. : H216-10-04568

SAMPLE RECEIVED DATE : 2010-09-07

TEST STARTED DATE : 2010-09-07

REPORT ISSUED DATE : 2010-09-09

PAGE : 1 OF 2

SAMPLE DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE WOVEN FABRIC.

BUYER'S NAME :


ITEM : POLYESTER FABIRC

ITEM NO. : ESCAPE1010

PO NO. : PY-12930

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY  
FOR FITI



SANG SOO, HAN  
QUALITY MANAGER

AUTHORIZED BY  
FOR FITI



MOON-OK NOH  
EXECUTIVE DIRECTOR

TEST CONDUCTED

TEST RESULT

(01) FLAMMABILITY ( CPAI 84, SECTION 6 WALL & TOP MATERIAL:1995 )

#1

AS RECEIVED

AFTER FLAME TIME(s)

- WARP 0 0 0 0 // 0

- WEFT 0 0 0 0 // 0

DRIP BURN(s)

- WARP 0 0 0 0 // 0

- WEFT 0 0 0 0 // 0

DAMAGED LENGTH(mm)

- WARP 158 163 154 161 // 159

- WEFT 149 137 141 136 // 141

NOTE) CONCLUSION : BASED UPON THE RESULTS OF THE TEST REPORT, THE SUBMITTED SAMPLE MEETS THE PERFORMANCE REQUIREMENTS FOR WALL AND TOP MATERIAL AS STATED IN CPAI 84, SECTION 3.2 IN ITS ORIGINAL STATE.

ACCEPTANCE CRITERIA

FABRIC WEIGHT(g/m <sup>2</sup> )	DAMAGED LENGTH(mm)		AFTER FLAME TIME(s)		DRIP BURN(s)	
	MAX. Avg.	Max. Ind.	MAX. Avg.	Max. Ind.	MAX. Avg.	Max. Ind.
MORE THAN 50 BUT NOT MORE THAN 135	215	255	2	4	0	0

SAMPLE :